

NEOTEX PU JOINT

Description of the product

One component polyurethane elastomer, suitable for sealing joints and openings in any building surface. After application, in contact with air, the sealant is vulcanised to an elastic and cohesive mass. Certified with CE according to EN 15651-1 (Type F EXT-INT CC).

Physical Properties

Neotex® PU Joint maintains its elasticity in a wide range of temperatures

It shows very good adhesion to many substrates, e.g. concrete, glass, anodized aluminum, wood, etc.

Easy application at temperatures from +5 °C to +40°C

Very good resistance to aging (UV and moisture).

High mechanical strength

Service temperature: -20°C to +90°C

Paintable

Technical characteristics

Colours	Grey/White
Skin forming time (23°C,50% RH)	120-240 min
Temperature of application	From +5°C up to +40°C
Service temperature	From -20°C up to +90°C
Curing speed (23°C,50% RH)	2-3 mm/day
Shore A Hardness (DIN 53 505)	30±5
Movement capability	25%
Tensile strength (ISO 8339)	0,82 N/mm ²
Modulus at 100% elongation (ISO 8339)	0,41 N/mm ²
Elastic recovery	>90%
Elongation at break (ISO 8339)	450 %

Application Fields

It is recommended for the sealing and bonding between similar and dissimilar substrates in traditional masonry, civil and industrial applications, light and heavy prefabrications, interior decorating etc.

Adheres on most substrates: concrete, glass, wood, anodised aluminium, tiles etc.

Instruction for use

Joint preparation: The joint faces to be bonded must be clean, dry and free from dust, oil, grease, old sealant and any traces of contaminant, which may affect adhesion. Surfaces should be degreased with solvent using a clean cloth. To remove dust, use oil-free compressed air.

Neotex[®] PU Joint

Priming: **Neotex[®] PU Joint** sealant does not normally require primer on most common substrates used in buildings. In cases of expansion joints with porous substrates (concrete), **Neotex[®] PU Primer** is recommended. The sealant is applied 15min to 1 hrs after the application of the primer.

Joint dimensions: The movement capability of sealant as well as local regulations must be considered. Joint width should be twice the depth when the width is bigger than 20mm and equal to the depth when the width is smaller than 20mm. The width of the joints should not be less than 5 and bigger than 40mm.

Sealant application:

- Cut the nozzle slantwise to form an opening proportional to the joint width.
- Put cartridge/sausage into the hand- or air gun and we apply the sealant in the joint.

For good performance it is essential that the sealant be only bonded to the two facing sides of the joint. To achieve this install a backup material (closed cell polyethylene or open cell polyurethane foam). Apply the sealant in a continuous operation making sure all air pockets or voids are eliminated. Tool the sealant with light pressure to spread the material against the joint surfaces.

This operation should be made with a dry spatula before skin formation occurs.

Excess uncured sealant should be wiped and cleaned with solvent **Neotex[®] 1111** cured sealant can only be removed by abrasion.

Notes

Low temperatures and high humidity during application prolong drying time, while high temperatures decrease it.

Packing

310ml cartridge
600ml sausage

Storage stability

The product is stable for 12 months when kept unopened in its original container, protected from humidity, at a maximum temperature of 30°C.



Al-Obour Buildings - Salah Salem Road - Nasr City - Cairo - Egypt.
10th Of Ramadan City.



info@CityChem.net



[@City_Chem](https://twitter.com/City_Chem)



[City Chem](https://www.facebook.com/CityChem)



+202 240 456 35



+2010 277 810 11



+2010 672 213 44

The Information Herein is Based on Our Present Knowledge and Experiences. This Information Merely Describes the Properties of Our Products but No Guarantee In the legal Sense Shall Be Implied. We Recommend Testing Our Products As To Their Suitability For Your Envisaged Purpose Prior To Use. No Warranties Of Any Kind, Either Express or Implied Including Warranties of Merchantability or Fitness For a Particular Purpose Are Made Regarding Any Products Mentioned Herein and Data or Information That Such Products, Data or Information May Be Used Without Infringing Intellectual Property Rights of Third Parties. We Reserve The Right To Make Any Changes According To Technological Progress or Further Developments. This Copy Replaces All Previous Versions - Printed in Egypt - 2020.



CONSTRUCTION